



we assist, advise and test

CTL®-No	369632/3
---------	-----------------

[Article]	sample of a pigment
[Product]	GE-233175 PIGMENT + BROWN-175. GOLDENEYE
[Batch-No]	07.2020 / 025

						passed
Azo-dyestuffs, Part 1a Investigation of aromatic amines with carcinogenic, mutagenic, reprotoxic and sensitising properties according to COE Resolution ResAP(2008)1 Methods acc. to § 64 LFGB 82.02-2,3,4,9 Detection limit: 1 ppm; limit: as low as technically avoidable						yes
Biphenyl-4-ylamine	-	4-Methoxy-m-phenylenediamine	-	4,4'-Methylenebis-(2-chloroaniline)	-	
Benzidine	-	4,4'-Methylenedianiline	-	4-Methyl-m-phenylenediamine	-	
4-Chloro-o-toluidine	-	3,3'-Dichlorobenzidine	-	o-Anisidine	-	
2-Naphthylamine	-	3,3'-Dimethoxybenzidine	-	4-Aminoazobenzene	-	
o-Aminoazotoluene	-	3,3'-Dimethylbenzidine	-	6-Amino-2-ethoxynaphthaline	-	
5-Nitro-o-toluidine	-	4,4'-Methylenedi-o-toluidine	-	4-Amino-3-fluorophenol	-	
4-Chloroaniline	-	6-Methoxy-m-toluidine	-			
Azo-dyestuffs, Part 1b Investigation of carcinogens classified in Categories 1, 2 and 3 by the European Commission and mentioned in the Council Directive 1967/548/EEC of 27 June 1967 according to EU Resolution ResAP(2008)1 Methods acc. to § 64 LFGB 82.02-2,3,4,9 Detection limit: 1 ppm						yes
4,4'-Oxydianiline	-	2,4,5-Trimethylaniline	-	2,6-Xylidine	-	
4,4'-Thiodianiline	-	Para-phenylenediamine	-			
o-Toluidine	-	2,4-Xylidine	-			



we assist, advise and test

CTL [®] -No	369632/3
----------------------	-----------------

[Article] sample of a pigment
 [Product] GE-233175 PIGMENT + BROWN-175.
 GOLDENEYE
 [Batch-No] 07.2020 / 025

			passed
Heavy metals, Part 3 acc. to COE Resolution ResAP(2008)1 Method: Prior, G. (2014). Tattoo Inks: Analysis, Pigments, Legislation. Berlin: epubli. CTL Method 2, p. 83.			yes
	Limit	Amount	
Arsenic (As)	2 ppm	< 2 ppm	
Barium (Ba)	50 ppm	< 50 ppm	
Cadmium (Cd)	0.2 ppm	< 0.2 ppm	
Cobalt (Co)	25 ppm	< 25 ppm	
Chromium (Cr), VI	0.2 ppm	< 0.2 ppm	
Copper (Cu), soluble	25 ppm	< 25 ppm	
Mercury (Hg)	0.2 ppm	< 0.2 ppm	
Nickel (Ni)	As low as technically achievable	< 0.5 ppm	
Lead (Pb)	2 ppm	< 2 ppm	
Selenium (Se)	2 ppm	< 2 ppm	
Antimony (Sb)	2 ppm	< 2 ppm	
Tin (Sn)	50 ppm	< 50 ppm	
Zinc (Zn)	50 ppm	< 50 ppm	